

P.14 series polyester smooth semimatt Colore®

The Information provided in this data sheet are generic for Colore® P.14 series. For further detail concerning specific products belonging to P.14 series, please contact us.

Description

Colore® P.14 Qualicoat homologated thermosetting powder coating formulated with polyester resin and light-resisting pigments. Film obtained after product's polymerization owns good resistance features concerning both atmospheric agents and chemical agents (detergents, propellants, lubricants ...).

Area of applicability

P.14 series, due to its chemical nature, is suggested for painting and protecting metallic substrates for outdoor use. Wide application field could be found in building sector, industrial automotive and standard accessories for common outdoor using.

Color / Aspect

Please check stock list for eventual availability. Minimum order for custom production, starting from 25

kgs.

Products developed in P.14 could be:

- Smooth – semimatt 31-50 gloss*
- Smooth – metallic/multicolor

Gloss level taken at 60° angle of incidence

Legislation

This powder coating respects European Directives "Restriction of the use of certain hazardous substances" 2002/95/CE and 2011/65/EU (RoHS).



P.14 series polyester smooth semimatt Colore®

Storage stability and packaging

if kept in dry environment, in sun shelter and at temperature of maximum less than 30° powder coating stays stable for 24 months. In presence of different conditions then the ones written above, it is possible to accuse inconveniences such as lumps and important decreasing in powder coating fluency.

Goods are supplied in 25 or 20 kgs plastic bags and cardboard boxes.



P.14 series polyester smooth semimatt Colore®

Physical features	
• Specific gravity:	1.20-1.60 g/cm ³ according to the product
• Theoretical spreading rate:	m ² /kg = 1000/specific weight for thickness
• Particle size at 63 μ:	range 20-26
• Minimum resin content:	60,00%

Features P.14 series after polymerization			
	Test conditions		
Steel panel	0,8 mm		
Surface pretreatment	Zinc salt phosphating		
Film thickness	According to the effect		
Curing conditions	180°x15' (T° object)		
TESTS	SPECIFICATIONS	UNIT OF MESAUREMENT	RESULTSI
Gloss (60°)	UNI EN ISO 2813	gloss	31-50
Thickness	UNI EN ISO 2360	μ	range 80-100
Color gap (Δe) compared to initial standard		CIEILab	according to Qualicoat specifications
Buchholz hardness	UNI EN ISO 2815		≥ 80 according to gloss level
Erichsen cupping test	UNI EN ISO 1520	mm	<5 mm no cracks
Impact test (concave)	UNI EN ISO 6272-2	cm/kg	25 cm/kg no cracks
Impact test (convex)	UNI EN ISO 6272-2	cm/kg	25 cm/kg no cracks
Bend test (Cylindered mandrel)	UNI EN ISO 6860	mm	7 mm No cracks
Cross-cut adhesion test	UNI EN ISO 2409	GT	0: no detachment
Salt spray test (1000 hrs)	MTD-03	mm	according to Qualicoat specifications
Solar box exposure (1000 hrs)	UNI EN ISO 11341	gloss	≤50% drop in gloss

Issued on 27/09/2022 Revision nr.9
This technical data sheet replaces all previous versions



P.14 series polyester smooth semimatt Colore®

Surface preparation

Surface must be carefully cleaned and degreased, according to the corrosion protection level requested. On steel, to get better results and to improve corrosion resistance features, it is possible and suggested, the use in combination with our Colore® epoxy primers.

Application

- Spraying can be done with automatic or manual Corona or Tribo electric system. With tribo electric system, compatibility with any metallic powder coating must be tested in plant, before its industrial use.
- Never mix powder from different production batches.
- The use of the same production batch is recommended on painting details that will be subsequently assembled.

Polymerization conditions

(object temperature)

- 180°x15'
- 190°x12'

Safety

Please check safety data sheet of specific product (MSDS)

Disclaimer: all provided and given information are correct and the result of our best experiences and knowledges, but they do not comport any responsibilities or warranty in case of non-proper use. In accordance with COLORE® policy of products development, information given in this technical data sheet are susceptible, without notice, of changing in respect of company view product's continuous improvement.

*Issued on 27/09/2022 Revision nr.9
This technical data sheet replaces all previous versions*

