

P.1 series epoxy-polyester Colore®

The Information provided in this data sheet are generic for Colore® P.1 series. For further detail concerning specific products belonging to P.1 series, please contact us.

Description

Colore® P.1 is an epoxy-polyester series, formulated with epoxy and polyester resins. It is heavy metals and TGIC free. Film obtained after product's polymerization owns good mechanical features, a good flow and valid resistant features to chemical agents (detergents, propellants, lubricants...)

Area of applicability

Products developed in P.1 series can be used for painting and protecting metallic substrates for indoor use: office and home furniture, household electric appliances, metal shelving, machine tools, etc....

Colour / Aspect

Please check stock list for eventual availability. Minimum order for custom production, starting from 25 kgs.

Products developed in P.1 could be:

- Smooth – glossy 80-95 gloss*
- Smooth – semi glossy 60-79 gloss*
- Smooth – metallic
- Fine structure – Matt
- Fine structure – metallic
- Rough structure – glossy
- Rough structure – semi glossy
- Rough structure – metallic

Gloss level taken at 60° angle of incidence

Legislation

This powder coating respects European Directives "Restriction of the use of certain hazardous substances" 2002/95/CE and 2011/65/EU (RoHS).

Storage stability and packaging

if kept in dry environment, in sun shelter and at temperature of maximum less than 30° powder coating stays stable for 24 months. In presence of different conditions then the ones written above, it is possible to accuse inconveniences such as lumps and important decreasing in powder coating fluency.

Goods are supplied in 25 or 20 kgs plastic bags and cardboard boxes.

Colore® - powder coatings

Versione 01/10/2015

This technical data sheet replaces all previous versions



P.1 series epoxy-polyester Colore®

Physical features	
•Specific gravity:	1.50-1.65 g/cm ³ according to the product
•Theoretical spreading rate:	m ² /kg = 1000/specific weight for thickness
•Particle size at 63 μ:	range 18-30

Features P.1 series after polymerization			
		Test conditions	
Steel panel	0,8 mm		
Surface pretreatment	Zinc salt phosphating		
Film thickness	According to the effect		
Curing conditions	180°x15' (T° object)		
TESTS	SPECIFICATIONS	UNITA' DI MISURA	RISULTATI
Gloss (60°)	UNI EN ISO 2813	gloss	Up to the effect
Thickness	UNI EN ISO 2360	μ	range 80-120
Colour gap (Δe) compared to initial standard		CIEILab	According to Qualicoat specifications
Buchholz hardness	UNI EN ISO 2815		Variable, according to the finishing (minimum value 80)
Erichsen cupping test	UNI EN ISO 1520	mm	<5 mm no cracks
Impact test (concave)	UNI EN ISO 6272-2	cm/kg	range 40-60 cm/kg no cracks
Impact test (convex)	UNI EN ISO 6272-2	cm/kg	range 50-70 cm/kg no cracks
Bend test (Cylindral mandrel)	UNI EN ISO 6860	mm	5mm No cracks
Cross-cut adhesion test	UNI EN ISO 2409	GT	0: no detachment
Salt spray test 250 h	MTD-03	mm	Penetratrion <2 mm

Colore® - powder coatings
 Versione 01/10/2015
 This technical data sheet replaces all previous versions



P.1 series epoxy-polyester Colore®

Surface preparation

Surface must be carefully cleaned and degreased, according to the corrosion protection level requested. On steel, to get better results and to improve corrosion resistance features, it is possible and suggested, the use in combination with our Colore® epoxy primers.

Application

- Spraying can be done with automatic or manual Corona or Tribo electric system. With tribo electric system, compatibility with any metallic powder coating must be tested in plant, before its industrial use.
- Never mix powder from different production batches.

Polymerization conditions

(object temperature)

- 170°x20'
- 180°x15'
- 190°x'10

Safety

Please check safety data sheet of specific product (MSDS)

Disclaimer: all provided and given information are correct and the result of our best experiences and knowledges, but they do not comport any responsibilities or warranty in case of non-proper use. In accordance with COLORE® policy of products development, information given in this technical data sheet are susceptible, without notice, of changing in respect of company view product's continuous improvement.

Colore® - powder coatings

Versione 01/10/2015

This technical data sheet replaces all previous versions

