

P.24 series epoxy pure Colore®

The information provided in this data sheet are generic for Colore® P.24 series. For further detail concerning specific products belonging to P.24 series, please contact us.

Description

Colore® P.24 is a high reactivity epoxy pure series, formulated with pure epoxy resins. It is heavy metals and TGIC free. Film obtained after product's polymerization owns good mechanical features and excellent resistant features to chemical agents (detergents, propellants, lubricants...) and remarkable protection against corrosion

Area of applicability

Products developed in P.24 series can be used only for painting and protecting metallic substrates for indoor use: office and house furniture, household electric appliances, metal shelving, machine tools, etc....

Colour / Aspect

Please check stock list for eventual availability. Minimum order for custom production, starting from 25 kgs.

Products developed in P.24 could be:

- Smooth – glossy 80-95 gloss*
- Smooth - metallic
- Fine structure – Matt
- Fine structure – metallic

Gloss level taken at 60° angle of incidence

Legislation

This powder coating respects European Directives "Restriction of the use of certain hazardous substances" 2002/95/CE and 2011/65/EU (RoHS).

Storage stability and packaging

if kept in dry environment, in sun shelter and at temperature of maximum less than 30° powder coating stay stable for 36 months. In presence of different conditions then the ones written above, it is possible to accuse inconveniences such as lumps and important decreasing in powder coating fluency.

Goods are supplied in 25 or 20 kgs plastic bags and cardboard boxes.



P.24 series epoxy pure Colore®

Physical features

- Specific gravity: 1.20-1.65 g/cm³ according to the product
- Theoretical spreading rate: m²/kg = 1000/specific weight for thickness
- Particle size at 63 µ: range 16-28

Features P.24 series after polymerization

Test conditions			
Steel panel	0,8 mm		
Surface pretreatment	Zinc salt phosphating		
Film thickness	According to the effect		
Curing conditions	160°x15' (T° object)		
TESTS	SPECIFICATIONS	UNIT OF MESAUREMENT	RESULTS
Gloss (60°)	UNI EN ISO 2813	gloss	Up to the effect
Thickness	UNI EN ISO 2360	µ	range 80-110
Colour gap (Δe) compared to initial standard		CIE Lab	According to Qualicoat specifications
Buchholz hardness	UNI EN ISO 2815		Variable, according to the finishing (minimum value 80)
Erichsen cupping test	UNI EN ISO 1520	mm	<4 mm no cracks
Impact test (concave)	UNI EN ISO 6272-2	cm/kg	range 40-50 cm/kg no cracks
Impact test (convex)	UNI EN ISO 6272-2	cm/kg	range 40-50 cm/kg no cracks
Bend test (Cylindral mandrel)	UNI EN ISO 6860	mm	7mm No cracks
Cross-cut adhesion test	UNI EN ISO 2409	GT	0: no detachment
Salt spray test (1000 hrs)	MTD-03	mm	corrosion length less than 2 mm



P.24 series epoxy pure Colore®

Surface preparation

Surface must be carefully cleaned and degreased, according to the corrosion protection level requested. On steel, to get better results and to improve corrosion resistance features, it is possible and suggested, the use in combination with our Colore® epoxy primers.

Polymerization conditions

(object temperature)

- 190°x'15

Application

- Spraying can be done with automatic or manual Corona or Tribo electric system. With tribo electric system, compatibility with any metallic powder coating must be tested in plant, before its industrial use.
- Never mix powder from different production batches.

Safety

Please check safety data sheet of specific product (MSDS)

Disclaimer: all provided and given information are correct and the result of our best experiences and knowledges, but they do not comport any responsibilities or warranty in case of non-proper use. In accordance with COLORE® policy of products development, information given in this technical data sheet are susceptible, without notice, of changing in respect of company view product's continuous improvement.

Colore® - powder coatings

Version 01/10/2015

This technical data sheet replaces all previous versions

