

## P.27 series PE GMA ULTRA MATT Colore®

The Information provided in this data sheet are generic for Colore® P.27 series. For further detail concerning specific products belonging to P.27 series, please contact us.

### Description

**Colore® P.27** is a thermosetting powder coating formulated with polyester resin properly catalyzed with GMA Acrylic Hardner and light-resisting pigments. Film obtained after product's polymerization owns good resistance features concerning both atmospheric agents and chemical agents (detergents, propellants, lubricants ...).

### Area of applicability

P.27 series, due to its chemical nature, is suggested for painting and protecting metallic substrates for outdoor use. Wide application field could be found in building sector, industrial automotive and standard accessories for common outdoor using. It is strongly suggested in the case of need of reaching extra matt gloss levels.

### Color / Aspect

Please check stock list for eventual availability. Minimum order for custom production, starting from 25 kgs.

Products developed in P.27 could be:

- Smooth –matt 0 - 5 gloss\*

*Gloss level taken at 60° angle of incidence*

### Legislation

This powder coating respects European Directives "Restriction of the use of certain hazardous substances" 2002/95/CE and 2011/65/EU (RoHS).

### Storage stability and packaging

if kept in dry environment, in sun shelter and at temperature of maximum less than 30° powder coating stay stable for 6 months. In presence of different conditions then the ones written above, it is possible to accuse inconveniences such as lumps and important decreasing in powder coating fluency.

Goods are supplied in 25 or 20 kgs plastic bags and cardboard boxes.



## P.27 series PE GMA ULTRA MATT Colore®

Physical features	
• Specific gravity:	1.20-1.60 g/cm <sup>3</sup> according to the product
• Theoretical spreading rate:	m <sup>2</sup> /kg = 1000/specific weight for thickness
• Particle size at 63 μ:	range 18-24
• minimum resin content:	60%

Features P.27 series after polymerization			
Test conditions			
Steel panel	0,8 mm		
Surface pretreatment	Zinc salt phosphating		
Film thickness	According to the effect		
Curing conditions	200°x15' (T° object)		
TESTS	SPECIFICATIONS	UNIT OF MESAUREMENT	RESULTS
Gloss (60°)	UNI EN ISO 2813	gloss	0-5
Thickness	UNI EN ISO 2360	μ	range 80-100
Colour gap (Δe) compared to initial standard		CIEILab	according to Qualicoat specifications
Buchholz hardness	UNI EN ISO 2815		No cracks
Erichsen cupping test	UNI EN ISO 1520	mm	<4 mm no cracks
Impact test (concave)	UNI EN ISO 6272-2	cm/kg	25 cm/kg no cracks
Impact test (convex)	UNI EN ISO 6272-2	cm/kg	25 cm/kg no cracks
Bend test (Cylindere mandrel)	UNI EN ISO 6860	mm	5 mm No cracks
Cross-cut adhesion test	UNI EN ISO 2409	GT	0: no detachment
Salt spray test (1000 hrs)	MTD-03	mm	according to Qualicoat specifications
Solar box exposure	UNI EN ISO 11341	gloss	≥50% drop in gloss



## P.27 series PE GMA ULTRA MATT Colore®

### Surface preparation

Surface must be carefully cleaned and degreased, according to the corrosion protection level requested. On steel, in order to get better results and to improve corrosion resistance features, it is possible and suggested, the use in combination with our Colore® epoxy primers.

### Application

- Spraying can be done with automatic or manual Corona or Tribo electric system. With Tribo electric system, compatibility with any metallic powder coating must be tested in plant, before its industrial use.
- Never mix powder from different production batches.

### Polymerization conditions

*(object temperature)*

- 200°x15'

### Safety

Please check safety data sheet of specific product (MSDS)

**Disclaimer:** all provided and given information are correct and the result of our best experiences and knowledges, but they do not comport any responsibilities or warranty in case of non-proper use. In accordance with COLORE® policy of products development, information given in this technical data sheet are susceptible, without notice, of changing in respect of company view product's continuous improvement.

Colore® - powder coatings

Issued on 30/06/2017

This technical data sheet replaces all previous versions

